



UV Pigment Dispersions

TRJ - 284 YELLOW PY 150

TRJ - 293 MAGENTA PR 122

TRJ - 288 CYAN PB 15 : 3

TRJ - 324 BLACK PK 7

TRJ - 738 WHITE PW 6

Here is UV curable pigment dispersion , It offer the simple preparation of inks and coatings by exposure to ultraviolet light or electron emitting sources. Typical these dispersions are 100 - 200nm , and 20- 25% wt of pigment. Other pigments and other monomers/blends are available on request. These dispersions are in NPEOGDA which is low odor , low skin irritation.

Light Fastness : 7 - 8 Alkali Resistnace : 8

